



## Touch Chem (M) Sdn Bhd

22, Jalan Anggerik Mocara 31/64,  
Kota Kemuning, 40460 Shah Alam,  
Selangor Darul Ehsan, Malaysia.

Tel : +603-5121 8802 Fax : +603-5122 1973

### Touch ANSET 3300

Oxidized Polyethylene Anti-Settling Agent for all solvent based coating.

#### Properties

Active Ingredient	:	24.0 – 25.0
Solvents	:	Xylene
Flash Point	:	24°C
Appearance behavior	:	Whitish high Thixotropic paste
Density	:	0.86 – 0.88 g/cm <sup>3</sup>

#### Description

**Touch ANSET 3300** are specially design as an anti-settling additives to use in all solvent based coating systems. It is based on linear structure Oxidized Polyethylene incorporated special function group for enhancing the hydrogen bonding effect that resulting in better anti-settling effect.

**Touch ANSET 3300** is a very thick whitish paste. The advantages of **Touch ANSET 3300** are as below:

- Prevent heavy pigments or filler to form hard settling
- No influence on gloss of a high gloss top coat
- Easy disperse to desire fineness
- Low dosage, high efficiency
- No seed out in the system after storage if incorporated in the system homogenously

#### Recommended For Use

**Touch ANSET 3300** is recommended for non-aqueous system. It can be use in all solvents based coating system. They are particularly suitable for:

- 1) Wood coating sealer or primer in NC, AC and Polyurethane.
- 2) Semi gloss and matted wood coating topcoat as a anti-settling for sanding materials like Zinc Stearate and Calcium Carbonate.
- 3) Epoxy primer and top coat.
- 4) Air dry alkyd primer.
- 5) Aerosol Paint and TPA system.
- 6) Baking paint primer.

#### Incorporation

We recommend to use in the pre-mix stage in order to have enough shear force to disperse them into the desire fineness. However customers also can prepared a easy dosing paste with below formulation in order to incorporate them in low shear force.

<b>Touch ANSET 3300</b>	50%
*Universal Resin (60% in Solid)	20%
Xylene	30%

\* Universal resin such as Laropal A81, Durapal A81 and etc for universal paste. However for use in only special system, you can use the resin in the system instead of the universal resin.

#### Dosage

0.2 – 1.0% based on total formulation.

#### Storage

**Touch ANSET 3300** is recommended to store in cool and dry place. Keep out of rain and direct sunlight.

#### Packaging

20kg & 170 kg non-returnable open top metal Container.